

| Production Location | | Regional Availability | Chemical Name | CAS Number | Typical %P | Formula Wt. | Food Contact | Recommended for: | | | | | | | | | | | | | | | | |
|---------------------|--------------|-----------------------|---|----------------------|------------|-------------|--------------|------------------|----|-----|----|------|-------|----|----------|-----|-----------|--------------|--------------|---------------------|--------|-------|------------------|-----|
| Galata EU | Galata US | | | | | | | PVC | PU | PET | PC | HDPE | LLDPE | PP | Acrylics | ABS | Adhesives | Epoxy Resins | Alkyd Resins | Lubricant Additives | Rubber | Nylon | Polyester Fibers | PBT |
| Mark CH 55 | | Global | Tris (nonylphenyl) Phosphite | 26523-78-4 | 4.2 | 689.0 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● |
| Mark TNPP | | Global | Tris (nonylphenyl) Phosphite, Stabilized | 26523-78-4, 122-20-3 | 4.2 | 689.0 | ✓ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ |
| | Weston DPP | Global | Diphenyl Phosphite | 4712-55-4 | 12.4 | 234.2 | | ○ | | | | | | | | ○ | | | | | | | | |
| Mark CH 66 | Weston TPP | Global | Triphenyl Phosphite | 101-02-0 | 10.0 | 310.3 | | ○ | ○ | ○ | ○ | ○ | | | | ○ | ○ | ○ | | | ○ | ○ | | ○ |
| Mark CH 300 | Weston PDDP | Global | Phenyl Diisodecyl Phosphite | 25550-98-5 | 7.1 | 438.6 | | ⊙ | ○ | | ○ | | | | | ○ | | | | | | | | |
| Mark CH 301 | Weston DPDP | Global | Diphenyl Isodecyl Phosphite | 26544-23-0 | 8.3 | 374.5 | | ⊙ | ○ | ○ | ○ | | | | | ○ | | | | | | | | |
| Mark CH 302 | Mark CH 302 | Global | Dodecyl Nonylphenol Phosphite Blend | Blend | 4.7 | 660.0 | | ⊙ | | | | | | | | | | | | | | | | |
| Mark CH 304 | Weston TDP | Global | Triisodecyl Phosphite | 25448-25-3 | 6.2 | 502.8 | | ○ | ○ | ○ | | ○ | | | | ○ | | | ○ | | | ○ | | |
| Mark CH 305 | | EU, AP | Triisotridecyl Phosphite | 77745-66-5 | 4.9 | 629.0 | | ○ | | | | | | | | | | | | | | | | |
| | Weston EHDP | AM, AP | 2-ethylhexyl Diphenyl Phosphite | 15647-08-2 | 9.0 | 346.4 | | ⊙ | | | | | | | ○ | | | | | | | | | |
| | Weston DHOP | Global | Poly (dipropylene glycol) Phenyl Phosphite | 80584-86-7 | 11.8 | 2,007.9 | | ○ | | | | | | | | | | | | | | | | |
| | Weston THOP | Global | Tetraphenyl Dipropylene glycol Diphosphite | 80584-85-6 | 10.9 | 566.5 | | ● | | | | | | | | | | | | | | | | |
| | Weston TLP | Global | Trilauryl Phosphite | 3076-63-9 | 5.3 | 587.0 | ✓ | ○ | | | | | | | | | | | ○ | | | ○ | | |
| | Weston PNPG | Global | Phenyl Neopentylene Glycol Phosphite | 3057-08-7 | 13.7 | 226.3 | | | | | ○ | | | | | | | | | | | | | |
| | Weston PTP | Global | Heptakis (dipropylene glycol) Triphosphite | 13474-96-9 | 9.1 | 1,185.2 | | | ○ | | | | | | | | | | | | ○ | ○ | | |
| | Weston TLTP | Global | Trilauryl Trithio Phosphite | 1656-63-9 | 4.9 | 635.2 | | | | | | ● | ● | ● | | | | | ● | | | | | |
| | Weston DPTDP | Global | Diphenyl Tridecyl Phosphite | 60628-17-3 | 7.4 | 416.2 | | ○ | | ○ | ○ | | | | | ○ | | | | | | | | |
| | Weston 430 | Global | Tris (Dipropylene glycol) Phosphite | 36788-39-3 | 7.2 | 430.5 | | | ● | | | | | | | | | | | | | | | |
| | Weston 437 | Global | Poly 4,4' Isopropylidenediphenol - C10 Alcohol Phosphite | 186270-40-6 | 6.0 | nd | | ○ | | | | | | | | | | | | | | | | |
| | Weston 439 | Global | Poly 4,4' Isopropylidenediphenol - C12-15 Alcohol Phosphite | 96152-48-6 | 5.6 | nd | ✓ | ⊙ | | | | | | | | | | | | | | | | |



| Regions Key | |
|-------------|--------------------------------|
| AM | North and South America |
| AP | Asia-Pacific |
| EU | Europe, Middle East and Africa |
| Global | Available World-wide |

| Symbols Key | |
|-------------|------------------------------|
| ● | Best fit |
| ⊙ | Good fit |
| ○ | Application dependent |
| ✓ | Check Applicable Regulations |

The information contained herein relates to a specific Galata product and its use, and is based on information available as of the date hereof. Additional information relating to the product can be obtained from the pertinent Material Safety Data Sheets. Nothing in this Technical Data Sheet shall be construed to modify any of Galata's standard terms and conditions of sale under which the product is sold by Galata. NOTHING IN THIS TECHNICAL DATA SHEET SHALL BE CONSTRUED TO CONSTITUTE A REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED REGARDING THE PRODUCT'S CHARACTERISTICS, USE, QUALITY, SAFETY, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall constitute permission or recommendation to practice any intellectual property without the permission of the owner.

Galata and the Galata logo are trademarks of Galata Chemicals, LLC or one of its subsidiaries.
Copyright © 2010 Galata Chemicals, LLC. All rights reserved.