



### Markstat® Antistatic Agent Product Guide

Product Name		Markstat 51	Markstat 60	Markstat AL-14	Markstat AL-26	Markstat AL-48a	Markstat AL-53
Regional Availability		EU	EU	AM	AM	AM	AM
Supply Form		L	L	L	L	L	L
Internal / External Application		I	I	I/E	I	I/E	I/E
FDA Sanctions				✓			✓
Viscosity at 25°C [20°C], cps		[51]	[250]	250	32	1800	
Composition:	Quaternary Salt				●	●	
	Polyether			●		●	●
	Polyethylene Glycoether	●	●				
Recommended for:	ABS			○	●	●	
	Acrylic			○	●	●	
	Cellulose Acetate			○		○	
	Cellulose Nitrate			○		○	
	Nylon			●		○	
	Polyacetal			○		○	
	Polyurethane			○		○	
	Polycarbonate			○		○	
	Polyethylene			○		○	
	Polypropylene			○		○	
	Polystyrene			●		○	●
	Flexible PVC	●	●	●	○	○	●
	Rigid PVC			○	●	●	●
Other Plastics			○		○	●	
Suggested loading, phr		1.0 - 8.0	1.0 - 8.0	3.0 - 7.0	0.5 - 3.0	0.5 - 3.0	1.0 - 5.0

Symbols Key	
●	Best fit
◎	Good fit
○	Application dependent
✓	Check Applicable Regulations

The information contained herein relates to a specific Galata product and its use, and is based on information available as of the date hereof. Additional information relating to the product can be obtained from the pertinent Material Safety Data Sheets. Nothing in this Technical Data Sheet shall be construed to modify any of Galata standard terms and conditions of sale under which the product is sold by Galata. NOTHING IN THIS TECHNICAL DATA SHEET SHALL BE CONSTRUED TO CONSTITUTE A REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, REGARDING THE PRODUCT'S CHARACTERISTICS, USE, QUALITY, SAFETY, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall constitute permission or recommendation to practice any intellectual property without the permission of the owner.

Galata and the Galata logo are trademarks of Galata Chemicals, LLC or one of its subsidiaries.  
Copyright © 2010 Galata Chemicals, LLC. All rights reserved.

